


INNOVATOR IN CELLENBETON

Binnenwand blokken

Blokken

60x25



	Blok 20	Blok 15	Blok 10	Blok 7	Blok 5
AFMETINGEN					
Lengte (cm) (Y)	60	60	60	60	60
Dikte (cm) (Z)	20	15	10	7	5
Hoogte (cm) (X)	25	25	25	25	25
KENMERKEN					
Tand en groef	enkel	enkel	enkel	enkel	nee
Handgrepen	ja	nee	nee	nee	nee
Uitsparing (cm ²)	-	-	-	-	-
Boring (cm)	-	-	-	-	-
Blokken/m ²	6,67	6,67	6,67	6,67	6,67
Palettisatie 120 x 120 x h (cm)	115	115	115	115	115
m ² /palet	7,20	9,60	14,40	20,40	28,80
lm/palet	-	-	-	-	-
Blokken/palet	48	64	96	136	192
Gewicht/palet (kg)	905	905	905	898	905
Gewicht blok bij levering (kg)	18,5	13,9	9,3	6,5	4,6
Lijmverbruik (kg/m ²)	3,4	2,5	1,7	1,2	1,2
Op stock/bestelling	stock	stock	stock	stock	stock
Cellumat code	BL20022	BL150B1	BL10013	BL07013	BL05013
EAN code	3700497016221	3700497010212	3700497013138	3700497012131	3700497011134
FYSISCHE EIGENSCHAPPEN					
Densiteitsklasse (kg/m ³)	C4/500	C4/500	C4/500	C4/500	C4/500
Min./max. droog gewicht (kg/m ³)	475-500	475-500	475-500	475-500	475-500
Karakteristieke druksterkte f_{bk} (N/mm ²)	4,0	4,0	4,0	4,0	4,0
Warmtegeleidbaarheid λ (W/mK)	0,135	0,135	0,135	0,135	0,135
Warmtegeleidbaarheid U (W/m ² K)*	0,59	0,76	1,05	1,38	1,73
Thermische weerstand R_{thu} (m ² K/W)*	1,69	1,32	0,95	0,73	0,58
Brandweerstand E.I. (min.)	360	240	120	90	-



(*) muur tweezijdig bepleisterd.